

ΕΚΤΥΠΩΣΙΜΟ ΟΛΟΓΡΑΦΙΚΟ ΙΡΙΔΙΖΟΝ ΑΥΤΟΚΟΛΛΗΤΟ 765

FILM	
Film Type	Holographic Film
Film Thickness (mils/μm)	6.0 / 152 (+/- 10%)
Film Weight (gsm)	190
Gloss (60°)	≥70
Opacity (%)	99
Tensile Strength (lbs/in)	N/A
Elongation (%)	N/A
Dimensional Stability (FTM 14)	MD ≤ 1.00 mm / CD ≤ 1.00 mm
ADHESIVE	
Adhesive Type	Emulsion Acrylic
Adhesive Thickness (mils/μm)	0.8-1.0 / 20-25
Adhesive Color	Clear
Peel Strength on Stainless Steel (lbs/in) / (N/25mm) 15 min	2.2 / 9.6
Peel Strength on Stainless Steel (lbs/in) / (N/25mm) 24 hrs	3.8 / 17
LINER	
Liner Weight (#/gsm)	90 / 145
Liner Type	White 2-side PE-Coated Kraft
Liner Thickness (mils/μm)	6.7 / 170
Release Force @ 360" / min (g/2")	70-100
PERFORMANCE GUIDANCE	
Application Temperature	≥ +50 °F
Service Temperature	-40 °F to 200 °F
Shelf Life	1 year
Storage Temp / Rel. Humidity	70 °F / 50%
Outdoor Durability	1 year
COMPATIBLE PRODUCTS	
Recommended Laminates	GF 108, GF 110, GF 231, GF 242, GF 247 or GF 400