

EXTERNAL APPLICATION

SOLAR FILMS SOL 116 SUN PROTECTION

TOTAL SOLAR ENERGY REJECTED : 86% **VISIBLE LIGHT TRANSMISSION :** 20% **REFLEXION SOLAR ENERGY:** 50% SOLAR ENERGY TRANSMISSION : 14% SOLAR ENERGY ABSORPTION : 36% 14% SOLAR FACTOR G : 99% UV BLOCK : PET SUPPORT : Polymer acrylic 19gr/m² ADHESIVE : SIlicosedPET 20 microns 67 **PROTECTOR:** microns **THICKNESS:** Silver metallic COLOUR: External **APPLICATION SIDE :** min, +°5C T° OF APPLICATION : EUROCLASSES **STANDARDS:** B-s1, d0 FIRE RATING : 5 years external **GUARANTEE :**

BY ROLL :

ENSIONS



METHOD OF APPLICATION


The surface to be bonded must be free from dust, grease or any other contaminant. Some materials, such as polycarbonate, can cause bubbling problems. A compatibility test is therefore recommended. Can be installed on plexiglass and polycarbonate.

PRODUCTION AND STANDARDS

1,83 x 30m

FORMATION

In order to constantly improve our products, we may modify colours and manufacturing processes without prior notice. Before applying our films, we recommend that users ensure that they are suitable for the intended use and comply with current standards.



Showroom : 36 rue Réaumur 75003 Paris

- Head office : P.A. des petits carreaux
 - 2 avenue des Orangers 94380 Bonneuil sur Marne France

86% SUN PROTECTION HEAT PROTECTION

DESCRIPTION

The SOL 116 has been designed to reduce heat and glare from the sun. The improvement in comfort is spectacular in premises flooded with sunlight. It is a real factor in improving comfort and saves energy when using air conditioning. **86% solar protection.**



SUSTAINABILITY : 10 years for vertical applications in Central Europe.

USE : For all types of glazing.

MAINTENANCE : After 30 days with a standard cleaning solution (non-abrasive, ammonia-free, etc.). Do not use cleaning products that could scratch the surface.

STORAGE : 2 years from delivery. This film should be stored away from excessive humidity and sunlight, at a temperature below 38°C.

In order to meet the highest standards, we recommend that you do not mix films from different productions.



. : +33 (0)1 43 99 00 22

: info@reflectiv.com

: www.reflectiv.com