



CORRIBOARD 3mm

Properties	Units	Values	Test Method
Grammature	g/m ²	900	
Thickness	mm	3	
Density	Kg/m ³	300	
Elastic Modulus	KPa	884	Iso 178
Resistance to bending	KPa	12,07	Iso 178
Dimensional variation	%	max 0,5	
Surface finishing		MATT 5 or SMOOTH	
Corona-treatment level	Dynes/cm	> 42	Tested with specific liquids for treatment-level measurement
Corona-treatment lifetime	month	3	
Delamination	N	min. 6 – Medium > 10	
Anti-UV Lifetime	Month	18	

- » Resistance to water, to heavy weather conditions, to oils and chemical products
- » The product is 100% recyclable (mono-materic)
- » Available treatment: Antistatic / Flame retardant

Tolerance	Weight	Thickness	Width	Length	Pallet Flatness
	± 5%	± 0,2 mm	± 2 mm	± 1%	max 30 mm